

# System 8

## Structural carbon steel



Structural carbon with an operating temperature of 80°C/176°F in internal, fully dry and well ventilated areas.

Pre-qualification is not required

Product	DFT (µm)
Hempel's Galvosil 15700	60
Hempadur 15570 (diluted 20 percent)	25
<b>Total</b>	<b>85</b>

Product	DFT (µm)
Hempadur Avantguard 860	60
Hempadur 15570 (diluted 20 percent)	25
<b>Total</b>	<b>85</b>

Product	DFT (µm)
Hempaprime Multi 500	150
<b>Total</b>	<b>150</b>

Product	DFT (µm)
Hempadur Avantguard 750	60
Hempadur 15570 (diluted 20 percent)	25
<b>Total</b>	<b>85</b>

Note 1: May be topcoated as required. Commonly used topcoats include:

- Hempaxane Light 55030
- Hempathane HS 55610
- Hempathane 55210
- Hempel's Pro Acrylic 55883
- Hempathane Speed-Dry Topcoat 250

This note applies to all of the above systems.

Note 2: As pre-qualification is not required additional systems may also be recommended. Contact your Hempel representative for further details.

Note 3: Avantguard® is a registered trademark of Hempel A/S.

For advice on regional product availability and additional schemes, please contact your local Hempel representative or email [protective@hempel.com](mailto:protective@hempel.com)

#### Hempel A/S

Lundtoftegaardsvej 91, 2800 Kgs. Lyngby, Denmark  
 Tel: +45 4593 3800 Email: [norsok@hempel.com](mailto:norsok@hempel.com)  
[norsok.hempel.com](http://norsok.hempel.com)